

Check / Change Wood Group Settings for MD and MD/C

(For complete manual see User Instructions 2.1 and 1.1)

Wait until mini-Ligno is off, then double click on-off switch between pins fast. Red number (2 or 3) indicates active setting. Click again to change setting. If the wood species is known use yellow species card to find correct setting. If you do not know the wood species or if you want to measure other materials, use the settings listed below. **If possible, measure dry material for comparison.**

Lignomat USA Ltd
 14345 NE Morris Ct.
 Portland OR, 97230 USA
 www.lignomat.com
 e-mail: sales@lignomat.com
 Tel: 800-227-2105
 503-257-8957

	Framing Lumber	Particle Brd Plywood Moldings	OSB	Hardwood Floors	Sheet-rock	Reference scale for other materials
Settings for MD, MD/C	3	3	2	2	2	2
Suggested Moisture Range**	below 19%	9-12%	9-12%	6-9%	6-11	WME Scale

Permissible Moisture Range** can vary by job, season, location.

Settings for mini-Ligno MD, MD/C

Woodgroup 2

Abachi
 Afrormosia
 Bamboo
 Beech
 Cedar (all types)
 Cumaru
 Dogwood
 Gonzales Alves
 Iroko
 Jatoba
 Koa
 Locust
 Oak Red / White
 Poplar
 Ramin
 Rosewood
 Teak
 Wenge
 Zebra Wood
 Hardboard
 OSB
 Waferboard

Woodgroup 3

Alder
 Ash
 Aspen
 Balsa
 Basswood
 Birch
 Cherry
 Cottonwood
 Cypress
 Elm
 Fir Douglas
 Gum
 Hemlock
 Hickory
 Kempas
 Larch
 Lauan (white / red)
 Mahogany
 Maple
 Meranti (dark / red)
 Merbau
 Myrtlewood
 Oak European
 Pine
 Pine Southern Yellow
 Redwood
 Spruce
 Tigerwood
 Walnut
 Particleboard